



Texan Stone LLC
DBA Texan Minerals and Chemicals

12814 Murphy Road, Stafford, TX 77477
 Phone: 713-294-4180 Email: Mani@TexanStone.com



India Best River Garnet 20-40 Mesh
Product Specification

Chemical Analysis		Sieve Analysis Report			
Elements	%	MM	ASTM	Retained(%)	Cum.(%)
SiO ₂	42-43	0.119	+16	0-1	0-1
Al ₂ O ₃	15-16	0.850	+20	8-10	9-11
Fe ₂ O ₃	32-33	0.710	+25	20-22	29-33
MgO	2-2.5	0.600	+30	20-24	49-55
CaO	2-3	0.500	+35	22-24	72-78
CaCO ₃	Absent	0.425	+40	12-14	88-90
TiO ₂	Absent	0.297	+45	10-12	90-100
LOI	0.32		Total	100	100

Mineral Composition		Physical Analysis	
Mineral	% by Weight	Test	Result
Garnet	98-99	Specific Gravity	4.2
Ilmenite	0.5-0.7	Bulk Density	2.3 gm/cm ³
Quartz	0.5-0.7	Hardness	8.3 Moh scale
Chemical Analysis			
Carbonates	Nil	Chloride	6-7 ppm
Nitrate	Nil	Sulphate	4 PPM
Conductivity	70 μ S/cm at 25.5 °C		

Standard Packing: 1,000 kgs (2,200 lbs.) or 2,000 kgs (4,400 lbs.) top and bottom spouted bulk bags with internal liner